

N&C

Slabstone Anti-slip



5 colours / 1 Finish / 3 Sizes

08452 606 028 | www.ncspecifier.com | samples@ncspecifier.com

Slabstone Anti-slip

Slabstone reminds us of the beauty of natural stone in its purest form. Keeping the personality traits of each of the natural stones, the Slabstone collection reinterprets them, giving them a sober and elegant character.



Slabstone Anti-slip

Slabstone reminds us of the beauty of natural stone in its purest form. Keeping the personality traits of each of the natural stones, the Slabstone collection reinterprets them, giving them a sober and elegant character.



Slabstone White Anti-slip



Slabstone Beige Anti-slip



Slabstone Tortora Anti-slip



Slabstone Light Grey Anti-slip



Slabstone Anti Slip

| | Test Method | Test Result | N&C Value |
|--|----------------|------------------------|-----------|
| Slip Resistance (Pendulum Test Values Rating) | BS 7976 | - | R11 |
| Water Absorption | EN ISO 10545-3 | > 0.03% < 0.1% | |
| Breaking Strength | EN ISO 10545-4 | ≥ 2300 N | |
| Modulus of Rupture | EN ISO 10545-4 | ≥ 40 N/mm ² | |
| Resistance to Abrasion | EN ISO 10545-4 | ≤ 139 mm ³ | |
| Length | EN ISO 10545-2 | According to the norm | |
| Width | EN ISO 10545-2 | According to the norm | |
| Thickness | EN ISO 10545-2 | According to the norm | |
| Straightness of Sides | EN ISO 10545-2 | According to the norm | |
| Squareness | - | - | |
| Surface Flatness | EN ISO 10545-2 | According to the norm | |
| Colour Resistance to Light Exposure | - | - | |

Chemical Properties

| | Test Method | Test Result | N&C Value |
|--|-----------------|-------------|-----------|
| Resistance to Acids (weak) | EN ISO 10545-13 | LA/LB | |
| Resistance to Acids (strong) | EN ISO 10545-13 | LA/LB | |
| Resistance to House Hold Cleaning Products | EN ISO 10545-13 | A | |
| Resistance to Staining | EN ISO 10545-14 | 4 | |