



Bedrock



Bedrock Fog

5 Colours / 1 Finish / 4 Sizes

Bedrock

With a slightly structured surface and a rich texture that must be seen and felt, it gives a natural and urban touch to modern and authentic environments.



Bedrock Dark

Bedrock

With a slightly structured surface and a rich texture that must be seen and felt, it gives a natural and urban touch to modern and authentic environments.



Bedrock Light

NCS189780 900x900x10.5mm
NCS189781 600x1200x10.5mm
NCS189782 600x600x8.8mm
NCS189783 300x600x8.8mm



Bedrock Silver

NCS189784 900x900x10.5mm
NCS189785 600x1200x10.5mm
NCS189786 600x600x8.8mm
NCS189787 300x600x8.8mm



Bedrock Fog

NCS189788 900x900x10.5mm
NCS189789 600x1200x10.5mm
NCS189790 600x600x8.8mm
NCS189791 300x600x8.8mm



Bedrock Dark

NCS189792 900x900x10.5mm
NCS189793 600x1200x10.5mm
NCS189794 600x600x8.8mm
NCS189795 300x600x8.8mm

Bedrock

With a slightly structured surface and a rich texture that must be seen and felt, it gives a natural and urban touch to modern and authentic environments.



Bedrock Gold

NCS189796 900x900x10.5mm
NCS189797 600x1200x10.5mm
NCS189798 600x600x8.8mm
NCS189799 300x600x8.8mm



Bedrock

Technical Specifications Physical properties

	Test of Norm	Value of Norm	N&C Value
Slip Resistance (Pendulum Test Values Rating)	BS 7976-2	PTV [0 – 100]	PTV = 32
Water Absorption	EN ISO 10545-3	$E \leq 0,5\%$	COMPLIANT
Breaking Strength	EN ISO 10545-4	≥ 1300 N	COMPLIANT
Modulus of Rupture	EN ISO 10545-4	≥ 35 N/mm ²	COMPLIANT
Resistance to Abrasion	EN ISO 10545-7	*According to tile colour	*According to tile colour
Length	EN ISO 10545-2	$\pm 0,6\%$	COMPLIANT
Width	EN ISO 10545-2	$\pm 0,6\%$	COMPLIANT
Thickness	EN ISO 10545-2	$\pm 5\%$	COMPLIANT
Straightness of Sides	EN ISO 10545-2	$\pm 0,5\%$	COMPLIANT
Squareness	EN ISO 10545-2	$\pm 0,5\%$	COMPLIANT
Surface Flatness	EN ISO 10545-2	$\pm 0,6\%$	COMPLIANT
Colour Resistance to Light Exposure	EN ISO 10545-16	*According to tile colour	*According to tile colour

Chemical Properties

	Test of Norm	Value of Norm	N&C Value
Resistance to Acids (weak)	EN ISO 10545-13	GLA–GLB–GLC	GLA
Resistance to Acids (strong)	EN ISO 10545-13	GHA–GHB–GHC	GHA
Resistance to House Hold Cleaning Products	EN ISO 10545-13	GA–GB–GC	GA
Resistance to Staining	EN ISO 10545-14	1-2-3-4-5	5