

N&C

Garda



Garda Warm Beige Rectified Porcelain Floor and Wall Tile 300x600mm

2 Colours / 1 Finish / 3 Sizes

08452 606 028 | www.ncspecifier.com | samples@ncspecifier.com

Garda

An exclusive collection of concrete-effect porcelain stoneware, in neutral tones.



Garda Ice White Rectified Porcelain Floor and Wall Tile 600x600mm

Garda

An exclusive collection of concrete-effect porcelain stoneware, in neutral tones.



Garda Light Grey Rectified Porcelain Floor and Wall Tile 600x600mm

Garda



Garda Ice White Rectified
Porcelain Floor and Wall Tile
300 x 600mm NB16000
600 x 600mm NB16006
600 x 1200mm NB16012



Garda Warm Beige Rectified
Porcelain Floor and Wall Tile
300 x 600mm NB16001
600 x 600mm NB16007
600 x 1200mm NB16013



Garda Taupe Grey Rectified
Porcelain Floor and Wall Tile
300 x 600mm NB16005
600 x 600mm NB16008
600 x 1200mm NB16014



Garda Mid Grey Rectified
Porcelain Floor and Wall Tile
300 x 600mm NB16003
600 x 600mm NB16009
600 x 1200mm NB16015

Garda



Garda Light Grey Rectified
Porcelain Floor and Wall Tile
300 x 600mm NB16004
600 x 600mm NB16010
600 x 1200mm NB16016



Garda Dark Grey Rectified
Porcelain Floor and Wall Tile
300 x 600mm NB16005
600 x 600mm NB16011
600 x 1200mm NB16017



Technical Specifications

Physical Properties

	Test of Norm	Value of Norm	N&C Value
Slip Resistance (Pendulum Test Values Rating)			
Water Absorbtion	average value <0.5 single value <0.6		0.005 0.006
Breaking Strength	>700 (THICKNESS <7.5MM) >1300 (THICKNESS >7.5MM)		2002
Modulus of Rupture	average value >35 single value >32		51.12 50.92
Resistance to Abrasion	175 MAX		118
Length			
Width			
Thickness			
Straightness of Sides			
Squareness			
Surface Flatness			
Colour Resistance to Light Exposure			

Chemical Properties

	Test of Norm	Value of Norm	N&C Value
Resistance to Acids (weak)			4days Hydrochloric acid 3% GLA 1day Citric acid 100g/l GLA 4days Potass hydrox 30g/l GLA
Resistance to Acids (strong)			
Resistance to House hold Cleaning Products	min. GB		1day Amm. Chlor. 100g/l GA 1day Hypochl. Sodi. 20mg/l GA
Resistance to Staining	>3		Chrome green in light oil 5 Iodine, alcoholic 5 Olive oil 5